< DUPONT >

DuPont[™] Kapton[®] 100CRC

Product Description

DuPont[™] Kapton[®] corona resistant film is a state of the art polyimide film that withstands the damaging effects of corona discharge.

The corona resistance of Kapton[®] 100CRC film provides improved service life and operational efficiencies beyond that of conventional insulation materials. In addition to the corona resistant properties, Kapton[®] CRC offers excellent, physical, electrical, thermal, and chemical resistant characteristics expected with Kapton[®] polyimide films. Kapton[®] CRC polyimide film has been developed for use as an electrically insulating material for high voltage environments where the potential for corona discharge is present. Kapton[®] CRC is typically used in industrial motor and generator applications as magnet wire, turn to turn strand, coil, slot liner and ground insulation materials. It has also been used to form laminates with other materials, such as DuPont[™] Nomex[®] paper or mica insulations, to provide a tailored electrical insulation property.

Applications


- AC Inverter Duty Motors
- Rail, Automotive Traction Motors
- Hydro, Wind Power Generators
- Transformers

Property	Unit	Typical Value	Test Method
Thickness —	mil	1	– ASTM D374
	μm	25.4	
Tensile Strength —	kpsi	33	– ASTM D882
	MPa	228	
Elongation	%	65	ASTM D882
Tensile Modulus —	kpsi	520	– ASTM D882
	GPa	3.6	
Dielectric Strength —	V/mil	6500	– ASTM D149
	kV/mm	256	
Dielectric Constant @ 1 kHz	-	3.4	ASTM D150
Dissipation Factor @1kHz	-	0.002	ASTM D150
Volume Resistivity	ohm-cm	>10 ¹⁶	ASTM D257
Yield —	ft²/lb	125	
	m²/kg	25.5	
Density	g/cc	1.55	ASTM D1505
UL Electrical RTI	°C	240	UL 746B
UL Mechanical RTI	°C	200	UL 746B
Flammability	UL-94	V-0	UL Test Method

Table 1 - Typical Physical Properties

Voltage Endurance of Film Subject to Partial Discharge Hours to Failure - ASTM D2275 -1/2" Diameter Electrodes, 5th out of 9

Figure 1–Comparison of Voltage Endurance, DuPont[™] Kapton[®] 100CRC to DuPont[™] Kapton® 100HN





kapton.com

DuPont products, please visit our website.

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. It may be subject to revision as new knowledge and experience becomes available. This information is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. Since we cannot anticipate all variations in end-use and disposal conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

For more information on DuPont[™] Kapton[®] or other

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Applications CAUTION" and "DuPont Medical Applications POLICY" statements. These documents are available upon request.

DuPont[®], the DuPont Oval Logo, and all products, unless otherwise noted, denoted with [®], ^{ee} or [®] are trademarks, service marks or registered trademarks of affiliates of DuPont de Nemours, Inc. Copyright © 2021 DuPont de Nemours Inc. All rights reserved.

EI-10175 (10/21)